




## Technical Data Sheet



### Maleic Acrylic Copolymer

Row	Parameter	Result
1	Appearance (25 °C)	Viscous Liquid
2	Dispersing capacity of Calcium Carbonate produced	Min 280
3	Dry matter (150 °C ) %	Min 40
4	Moisture %	56 – 60
5	PH 10 %	7.5 – 9
6	Viscosity (20 °C) (CP)	1500 – 3000

**CAS Number:** 29132-58-9, 26677-99-6

**Synonyms:** Poly (acrylic acid-co-maleic acid), MA/AA, Poly(acrylic acid-co-maleic acid) solution, Acrylic acid maleic acid copolymer, Acrylic acid, polymer with maleic anhydride Poly (maleic anhydride-acrylic acid copolymer), Acrylic acid maleic anhydride copolymer Copolymer Maleic Acid and Acrylic Acid, Copolymer of Maleic and Acrylic Acid, Acrylic Acid Maleic Acid Copolymer

**Applications:** Used in low phosphate or phosphate-free formulas in laundry industrial and industrial dishwashers to control the formation of insoluble materials and to preserve the whiteness of the fabric. It is a good choice for a water softener based on any type of hydrated silicate.

